

Innovadex® Product Datasheet

Lamesoft® PO 65

PRD 30528377

Valid since	14.03.2013
Revision	1.0
WF-No.:	1628
Page	1 of 3

® = registered trademark of BASF

™ = Trademark of BASF

Care Chemicals**General characterisation****Chemical description**

Mixture of alkyl glucoside with fatty acid glyceryl ester

Raw material basis

Vegetable:

(coconut / palm kernel oil, sunflower oil, glucose, glycerine)

Labeling information**INCI name(s)**

Coco-Glucoside (and) Glyceryl Oleate

Ingredient information**Ingredient**

Coco-Glucoside

Glyceryl Oleate

CASR-No.

141464-42-8

68424-61-3

EINECS/ELINCS-No.

no longer Polymer / TSCA

270-312-1

Product properties**Appearance**

Transparent to slightly yellowish viscous product with characteristic odor

Example of use

The product is preferably used as lipid layer enhancer for the production of surfactant cleansing preparations. On account of its viscosity-increasing properties Lamesoft® PO 65 contributes to the viscosity formation in cosmetic cleansing preparations such as shower gels, foam baths, shampoos and baby products. The presence of the dermatological high value alkyl poly glycoside contributes with approx. 1.7 % to the final washing active substance considering a dosage of 5 % Lamesoft® PO 65. Correspondingly the amount of the basic or secondary surfactant can be reduced.

Innovadex® Product Datasheet

Lamesoft® PO 65

PRD 30528377

Valid since	14.03.2013
Revision	1.0
WF-No.:	1628
Page	2 of 3

® = registered trademark of BASF

™ = Trademark of BASF

Care Chemicals**Characteristic values**

The specifications stated in the paragraphs 'Quality control data' and 'Additional product descriptive data' finally and conclusively describe the properties of the product.

Quality control data

(Data which is used for quality release and is certified for each batch.)

Odor evaluation versus standard	corresponds to the standard	
Visual appearance versus standard	corresponds to the standard	
Water content	32.0 - 35.0 %	DGF H-III 3A
Density (20 °C)	1.06 - 1.10 g/cm³	DIN 51757 V4
Viscosity Brookfield (20 °C)	2500 - 6000 mPas	ASTM D 2196
pH value (5 %)	3.0 - 4.0	DGF H-III 1

Additional product descriptive data

(Data which is proven statistically but not determined regularly.)

Dry residue	64.0 - 68.0 %	DGF G-III 1
-------------	---------------	-------------

Stabilising additives / Auxiliaries

(type and concentration)

Preservatives

not present

Innovadex® Product Datasheet

Lamesoft® PO 65

PRD 30528377

Valid since	14.03.2013
Revision	1.0
WF-No.:	1628
Page	3 of 3

® = registered trademark of BASF

™ = Trademark of BASF

Care Chemicals**Storage information****Shelf life**

12 months

Storage temperature

Between + 10 °C and + 30 °C

Storage conditions

In original sealed containers and protected from moisture.

Additional information

The product is preferably processed at temperatures between 15 and 25 °C. Storage at temperatures below 10 °C can lead to a crystallization. This property is characteristic of the product and reversible by stirring and heating at 25 - 40 °C. Prolonged storage and transportation of this material at temperatures > 30 °C can lead to an increase in the viscosity which has no effect on the efficacy of Lamesoft PO 65. Only the handling must be adjusted appropriately when the viscosity has increased (while stirring the viscosity can increase). Containers and storage tanks made of steel (material no. 1.4571) are suitable for storing Lamesoft® PO 65. The product is protected against oxidation through addition of mixed tocopherols.

Disclaimer

This document, or any answers or information provided herein by BASF, does not constitute a legally binding obligation of BASF. While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. It does not relieve our customers from the obligation to perform a full inspection of the products upon delivery or any other obligation. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.